



Rollei INFRARED

Special infrared film up to 820 nm. High sensitivity at ISO 400 without filtering. Excellent tonality, resolving power by 160 Lp/mm. Special AURA effects by over exposing film.

The ROLLEI INFRARED is well suited for experimental, creative applications, and for scientific photography. Perfect exposures can be reached, using special infrared filters, leading into results with an unusual tonal range.

Characteristics and application:

- high speed panchromatic b&w film material with special infrared sensitivity;
- large exposure latitude and an high exposure reserve for application under all lighting and climatic conditions;
- special coating for improvement of film transport properties of the cameras;
- suitable for daylight and tungsten light conditions;
- table polyester base support guarantees the highest level of archive stability (LE 500);
- the large contrast power, in addition of very fine grain and excellent sharpness, is the basis for negatives of excellent quality;
- excellent resolving power, very fine grain and high sharpness as a base for negatives with an excellent quality;
- especially suited for digital application for scanning;
- special halation effects (AURA effect) by longer exposure times;

Note: Under careful handling, the ROLLEI IR 400 can be inserted and removed from the camera, under subdued light conditions!

Film base: Accurate, tear-proof clear polyester material, 100µm, 35mm, rollfilm and cut sheet film material.

Film layer

- emulsion side: protective layer + emulsion layer + polyester base 100µm
- back side: NC = none curling coating

Layer thickness: w/o layers 7,5µm

Grain thickness: RMS (x1000) 11.0 with Refinal developer, 5 Min, 20° C

Speed:

ISO 400/27°

Resolving power:


contrast-1000:1 lines/mm-160

Reciprocity effect


Reading of exposure in sec.: 1/10,000 - 1/2

Exposure compensation in steps: N/A Compensation of development time: N/A

Characteristic diagram:



Spectral sensitivity:



Storage:

It is recommend not to leave the film material exposed into direct sunlight, strong heat or relative high humidity.

Cooled stored film material should not be used until film will be warmed up to ambient temperature.

- unexposed film: Up to 24 months in cold storage by 8° C is recommend
- exposed film: After exposure, please keep film in cold condition, processing as soon as possible is recommend

Processing:

The ROLLEI INFRARED must be processed in complete darkness! He can be developed sucessfully in all standard developers, such as AGFA, ILFORD, KODAK, LABOR PARTNERS or TETENAL. To achieve optimal results, a test development is recommended in order to obtain the right development times and temperatures. By using other brands of developers -not tested by MACO- decreases of quality can be expected showing rough grain structures and low sensitivity.

Application of special infrared filters:

RG 715 (HELIOPAN), #88A (KODAK) real sensitivity 25/15°

In order to exclude failure photographs as source of error, it is recommended to release to each exposure row a non filtered shot with this film, exposed like a panchromatic film with a sensitivity of ISO 400/27° .

The development time chart can be found in the internet under www.rollei.com.

Packing:

35mm	135 – 36	prof. pack of 10	Artikel No.: RI4011P
Rollfilm	120	prof. pack of 12	Artikel No.: RI4001P
Sheet film	4" x 5"	25 sheets	Artikel No.: RI410
ROLLEI photo chemistry	HIGH SPEED	1 + 7	Artikel No.: RHS11
	SHORT STOP	1 + 16	Artikel No.: RSS11
	FIXIERER	1 + 7 – 1 + 9	Artikel No.: RFX11
	WETTING AGENT	1 + 1.000	Artikel No.: RWA12